



TECHNICAL DATA SHEET

ISOBENT® M5000

Mokarrar Composite Co.: No.23, 64 St, Yousef Abad Ave., Tehran, Iran
 Tel.: +98 (21) 8860 22 78-9 Fax: +98 (21) 8860 22 80
 www.geo-mokarrar.com info@geo-mokarrar.com

Property	Test Method	Frequency	Unit	ISOBENT® M5000
BENTONITE				
Swell Index	ASTM D-5890	50 Tonnes	ml/2g	>27
Fluid Loss	ASTM D-5891	50 Tonnes	ml	< 16
Non-Woven Geotextile				
Type	Polypropylene			
Mass Per Unit Area	ASTM D-5261	20,000 m ²	g/m ²	300
Woven Geotextile				
Type	Polypropylene			
Mass Per Unit Area	ASTM D-5261	20,000 m ²	g/m ²	130
GCL				
Mass Per Unit Area	ASTM D-5993	4,000 m ²	g/m ²	5000
Thickness	EN ISO 9863-1	20,000 m ²	mm	6
Moisture Content	ASTM D-5993	4,000 m ²	%	10
Tensile Strength-MD	ASTM D-6768	20,000 m ²	kN/m	8
Peel Strength	ASTM D-6496	4,000 m ²	N/m	500
Permeability	ASTM D-5887	25000 m ²	m/sec	1 × 10 ⁻¹¹
Index Flux	ASTM D-5887	25000 m ²	m ³ /sec-m ²	1 × 10 ⁻⁸
Permeability against Cacl ₂ permeate				
At 35 KPa	ASTM D-6766	Yearly	m/sec	8.3 × 10 ⁻¹⁰
At 500 KPa	ASTM D-6766	Yearly	m/sec	1.5 × 10 ⁻¹¹
Supply Specifications				
Roll Dimension - Width	4 ⁽¹⁾		m	
Roll Dimension - Length	30 , 40 , 50 ⁽¹⁾		m	
Area (Surface-Roll)	120, 160, 200		m ²	

(1) Length/width of the roll according to customer's requirements

All information contained here is believed to be accurate, but is not warranted. It does not represent any assurance of properties and fitness for use of the product. The above mentioned specifications may be changed without any notice.